

TABOREN PH 43 T 20-009



Description

TABOREN PH 43 T 20-009 is a compound based on polypropylene homopolymer, filled with 20% of talc and stabilized with an UV additive package. It is designed for injection moulding technology and used in automotive applications requiring outstanding performance under enhanced temperatures.

The grade is available in standard black colour.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS

Physical	Melt Flow Index (230°C / 2,16 kg)	ISO 1133	g/10 min	3,0
	Density	ISO 1183-1	g/cm ³	1,04
Mechanical	Tensile Strength at Yield	ISO 527	MPa	30
	Charpy Notched Impact Strength	ISO 179-1/1eA 23°C	KJ/m ²	3
	Charpy Unnotched Impact Strength	ISO 179-1/1eU 23°C	KJ/m ²	30
	Elongation at Break	ISO 527	%	15
	Flexural Modulus	ISO 178	MPa	3100
Thermal	VICAT Softening Temperature	ISO 306 method A50	°C	150

Notes* The above values are typical for this material, not standardized.

TABOREN PH 43 T 20-009



Processing Guidelines

Drying

TABOREN PH 43 T 20-009 is recommended to be pre-dried before processing. A guideline is to dry the grade at 80°C for 3 hrs.

Machine Requirements:

TABOREN PH 43 T 20-009 is easy to process on standard injection moulding machines. The following moulding parameters are to be used as guidelines:

Melt Temperature:	200 - 250 °C
Injection Speed:	Medium
Injection Pressure:	90 - 130 MPa
Hold-on Pressure:	>40% of injection pressure
Mould Temperature:	30 - 50 °C

Storage and handling

TABOREN PH 43 T 20-009 should be stored in dry conditions at temperatures below 50°C and protected from UV light. Improper storage may initiate degradation resulting in odour generation and colour changes a can have negative effects on the physical properties of the product.

Safety

TABOREN PH 43 T 20-009 is not classified as a dangerous preparation. A Safety Datasheet is available on request. Please contact your SILON representative for more details.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS