

TABOREN-PR 73 T 10S-094



Description

TABOREN-PR 73 T 10S-094 is a compound based on mixture of polypropylene block copolymer and POE, filled with 10% of talc and stabilized with a basic antioxidant package. Additionally it contains an UV and anti-scratch additives. It is designed for injection moulding technology and used in many industrial fields with stress put on excellent processability and good surface performance. The grade is available in black colour.



**AUTOMOTIVE
APPLICATIONS**



**CONSTRUCTION
APPLICATIONS**



**GENERAL
APPLICATIONS**



**HYGIENIC
APPLICATIONS**

Properties		Test method	Unit	Typical value
Physical	Melt Flow Index (230°C / 2,16 kg)	ISO 1133	g/10 min	12,0
	Density	ISO 1183-1	g/cm ³	0,960
Mechanical	Tensile Strength at Yield	ISO 527	MPa	15
	Charpy Notched Impact Strength	ISO 179-1/1eA 23°C	KJ/m ²	60 P.B.
	Charpy Unnotched Impact Strength	ISO 179-1/1eU 23°C	KJ/m ²	N.B.
	Elongation at Break	ISO 527	%	50
	Flexural Modulus	ISO 178	MPa	1100
Thermal	VICAT Softening Temperature	ISO 306 method A50	°C	121

Notes* The above values are typical for this material, not standardized.

TABOREN-PR 73 T 10S-094



Processing Guidelines

Drying

TABOREN-PR 73 T 10S-094 is recommended to be pre-dried before processing. A guideline is to dry the grade at 80°C for 3 hrs.

Machine Requirements:

TABOREN-PR 73 T 10S-094 is easy to process on standard injection moulding machines. The following moulding parameters are to be used as guidelines:

Melt Temperature:	200 - 250 °C
Injection Speed:	Medium
Injection Pressure:	90 - 130 MPa
Hold-on Pressure:	>40% of injection pressure
Mould Temperature:	30 - 50 °C

Storage and handling

TABOREN-PR 73 T 10S-094 should be stored in dry conditions at temperatures below 50°C and protected from UV light. Improper storage may initiate degradation resulting in odour generation and colour changes a can have negative effects on the physical properties of the product.

Safety

TABOREN-PR 73 T 10S-094 is not classified as a dangerous preparation. A Safety Datasheet is available on request. Please contact your SILON representative for more details on various aspects of safety.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.



**AUTOMOTIVE
APPLICATIONS**



**CONSTRUCTION
APPLICATIONS**



**GENERAL
APPLICATIONS**



**HYGIENIC
APPLICATIONS**