



# TABOREX TA 2170 CL

## Catalyst masterbatch

### Description

**TABOREX TA 2170 CL** contains the cross-linking catalyst and a stabilizer package. Together with SILON's Silane grafted TABOREX Compound this masterbatch completes a Sioplas System (PE-Xb). TABOREX TA 2170 CL is especially designed to reduce degradation caused by disinfection in potable water systems.

**Appearance:**

Opaque

**Physical form:**

Pellets

### Application

**TABOREX TA 2170 CL** is a catalyst Masterbatch according to the Sioplas System for the production of pipes for sanitary and heating applications.

### Addition level

Catalyst masterbatch and grafted polymer are normally being mixed in the ratio of 95 parts of polymer to 5 parts of catalyst MB. This formulation insures optimum processing conditions and application performance of the PE-X material.

### Properties

	Properties	Test method	Unit	Typical value
Physical	Density	ISO 1183-1	g/cm <sup>3</sup>	0,964
	Melt Flow Index (190 °C/2,16 kg)	ISO 1133	g/10 min	9,0
	Bulk density	ISO 60	g/cm <sup>3</sup>	0,53
	Moisture (water)	ISO 15512	%	< 0,25

**Note:** the above values are typical for this material, not standardized.



AUTOMOTIVE  
APPLICATIONS



CONSTRUCTION  
APPLICATIONS



GENERAL  
APPLICATIONS



HYGIENIC  
APPLICATIONS

# TABOREX TA 2170 CL



## Packaging

- moisture resistant multilayer bags containing 20 kg
- boxes of 600 kg containing a moisture resistant multilayer lining

## Storage and handling

**TABOREX TA 2170 CL** has to be stored in a cool and dry place, protected from direct UV light. At a maximum ambient temperature of 30 °C the shelf life is one year. Storage at higher temperatures may impair the quality of the Masterbatch.

## Food contact

**TABOREX TA 2170 CL** corresponds to the regulations of the European Union, FDA(USA) and BfR (Germany) for products intended to use in contact with drinking water.



AUTOMOTIVE  
APPLICATIONS



CONSTRUCTION  
APPLICATIONS



GENERAL  
APPLICATIONS



HYGIENIC  
APPLICATIONS