



TABOREX TA 2147 HD

Catalyst masterbatch

Description

TABOREX TA 2147 HD contains the cross-linking catalyst and a stabilizer package. In addition it carries additives that protect the polymer from degradation caused by Metal Ions. Together with SILON's Silane grafted TABOREX Compound this masterbatch completes a Sioplas System (PE-Xb).

Appearance :
Opaque

Physical form:
Pellets

Application

TABOREX TA 2147 HD is a catalyst Masterbatch according to the Sioplas System for the production of pipes for sanitary and heating applications. TABOREX TA 2147 HD is specifically designed for the use in heterogenous pipe systems or in systems using brass fittings for pipe jointing.

Addition level

Catalyst Masterbatch and graft polymer are normally being added in the ratio of 95 parts of graft to 5 parts of catalyst MB. This formulation insures optimum processing conditions and application performance of the PE-X material.

Properties

	Properties	Test method	Units	Typical Value
Physical	Density	ISO 1183-1	g/cm ³	0,970
	Melt Flow Rate (190°C/2,16 kg)	ISO 1133	g/10 min	9,0
	Bulk density	ISO 60	g/cm ³	0,55
	Moisture (water)	ISO 15512	%	<0.25

Notes* The above values are typical for this material, not standardized.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS



Packaging

- moisture resistant multilayer bags containing 20 kg
- boxes of 600 kg containing a moisture resistant multilayer lining

Storage

TABOREX TA 2147 HD has to be stored in a cool and dry place. At a maximum room temperature of 25°C the storage life is one year. Storage at higher temperatures may impair the quality of the Masterbatch.

Food contact

TABOREX TA 2147 HD corresponds to the regulations of the European Union, FDA(USA) and BfR (Germany) for products intended to use in contact with drinking water.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS