

TABOREN-PC 42 B 35-630

Description

TABOREN-PC 42 B 35-630 is a compound based on block polypropylene copolymer filled with 35% of barium sulfate, stabilized with a basic antioxidant package. It is suitable for extrusion and blow moulding applications in many industrial fields with stress put on excellent processability and good surface performance. The grade is available in blue colour.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS

Physical	Melt Flow Index (230°C / 2,16 kg)	ISO 1133	g/10 min	1,5
	Density	ISO 1183-1	g/cm ³	1,23
Mechanical	Tensile Strength at Yield	ISO 527	MPa	18
	Charpy Notched Impact Strength	ISO 179-1/1eA 23°C	KJ/m ²	10
	Charpy Unnotched Impact Strength	ISO 179-1/1eU 23°C	KJ/m ²	n.b
	Flexural Modulus	ISO 178	MPa	1.700
Thermal	VICAT Softening Temperature	ISO 306 method A50	°C	145

Notes* The above values are typical for this material, not standardized.

TABOREN-PC 42 B 35-630



Processing Guidelines

Drying

TABOREN-PC 42 B 35-630 is recommended to be pre-dried before processing. A guideline is to dry the grade at 80°C for 3 hrs.

Machine Requirements:

TABOREN-PC 42 B 35-630 can be processed without problems on all extrusion lines suitable for production of PP profiles and pipes.

Screw:

Abrasion protected coating of the screw is recommended due to the content of filler.

Length: 25D – 30D

Heating:

At least three separately controllable heating zones. The cylinder flange and adapter must be able to be heated.

Temperature Profile:

Hopper:	15 – 40°C
Zone 1:	180 – 190°C
Zone 2:	190 – 200°C
Zone 3:	200 – 210°C
Adapter:	200 – 210°C
Die:	200 – 210°C
Melt:	200 – 210°C



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS

TABOREN-PC 42 B 35-630

Storage and handling

TABOREN-PC 42 B 35-630 should be stored in dry conditions at temperatures below 50°C and protected from UV light. Improper storage may initiate degradation resulting in odour generation, colour changes and could have negative effects on the physical properties of the product.

Safety

TABOREN-PC 42 B 35-630 is not classified as a dangerous preparation. A Safety Datasheet is available on request. Please contact your SILON representative for more details on various aspects of safety, recovery and disposal of the product or see our web pages www.silon.eu

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.



AUTOMOTIVE
APPLICATIONS



CONSTRUCTION
APPLICATIONS



GENERAL
APPLICATIONS



HYGIENIC
APPLICATIONS